LASERLUX®

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	90-110 microns	Siliconized paper	REACH compliant VEGANOK AZIENDA N. 1004

APPLICATION INSTRUCTIONS

Applies on	TRANSFER SETTINGS			
	Time	Temperature	Pressure	Peel
cotton, polyester, poly/cotton blends	15 seconds	150°C (302°F)	Medium (2,5/3,5 bar)	hot/cold

→ **Decorate or cut the material following the instructions for your laser cutting plotter**
→ **Peel off any excess material**
→ **Remove the print from the backing using the LASERLUX MASK.**
→ **Position the decoration on the fabric**
→ **Apply according to the recommended parameters.**
→ **Remove the LASERLUX MASK whilst hot or cold**

HIGHLIGHTS
→ **Vibrant colours**
→ **Iridescent textures**
→ **Specifically designed for laser engraving**

NOTE: We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, inside-out	YES inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

→ **Wait 24 hours after the application before the first wash**
→ **Respect the textile recommendations**
→ **Do not bleach or use aggressive chemical agents**

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it

Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246

TÜVRheinland CERTIFIED
Management System ISO 9001:2015 ISO 14001:2015
www.tuv.com ID 9105027958